SHANGHAI
5F Annex Dragon Pearl Plaza
2123 Pudong Avenue
Shanghai 200135 - P.R. CHINA
Tél. : +86 21 68 55 50 32
Fax : +86 21 68 55 50 33
E-mail : ctcshanghai@ctcgroupe.com

TEST REPORT

Report No.: S150805846_1

08/17/2015

APPLICANT: 安思尔（上海）商贸有限公司（C30663）

上海市中山西路1600号宏汇大厦1号楼903-905室

Date of receipt :08/11/2015
Testing period :08/14/2015
:08/14/2015

Buyer: --

Sample description: EDGE 48-125 白色


Test(s) requested	:--
Service	:REGULAR
Brand / Section	:--
Season	:--
End use	:--
Factory name	:--
Factory code	:--

For CE Marking : Yes

Previous report	:--
Product category	:--
Product type	:--
Test stage	:FIRST TEST
Supplier name	:--
Exported to	:--

1. Conclusion:

Approved by



Henry YAN
Laboratory Supervisor

The report is issued by CTC Shanghai under its General Conditions printed overleaf. The results shown in this report refer only to the sample (s) tested. Except by special arrangement, the test items will not be retained by CTC Shanghai for more than 6 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.

Report No.: S150805846_1 08/17/2015

APPLICANT: 安思尔（上海）商贸有限公司（C30663）

2. Sample(s) description assigned by laboratory:

Size	Analyzed product	Description	Sample information
	glove	palm	



150805846

The report is issued by CTC Shanghai under its General Conditions printed overleaf. The results shown in this report refer only to the sample (s) tested. Except by special arrangement, the test items will not be retained by CTC Shanghai for more than 6 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.

Report No.: S150805846_1 08/17/2015

APPLICANT: 安思尔（上海）商贸有限公司 (C30663)

3. glove/

palm

	Method	Unit	Result
Abrasion resistance	GB 24541-2009		
Number of cycles to breakthrough - Lowest value		cycles	8000
Performance Level			Level 4
Tear resistance	GB 24541-2009		
Total torn tearing force - Lowest value		N	68
Performance Level			Level 3
Puncture resistance	GB 24541-2009		
Force recorded - Lowest value		N	28
Performance Level			Level 1
Blade cut resistance	GB 24541-2009		
I1		Index	2.1
I2		Index	2.4
I3		Index	2.3
I4		Index	1.8
I5		Index	1.8
I1(2)		Index	2.3
I2(2)		Index	2.4
I3(2)		Index	2.7
I4(2)		Index	2.3
I5(2)		Index	2.3
Imean(2)		Index	2.4
Performance level			Level 1

END OF TEST REPORT

The report is issued by CTC Shanghai under its General Conditions printed overleaf. The results shown in this report refer only to the sample (s) tested. Except by special arrangement, the test items will not be retained by CTC Shanghai for more than 6 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.